


## TuffCut® XT

### 278 / 278CB / 278N Series Recommended Cutting Data - Profile Milling - Inch

Workpiece Material Group	ISO	Hardness	Coolant ● Preferred ○ Possible x Not Possible			Profiling (ae)*				End Mill Diameter (inch)								
										1/8*	3/16*	1/4*	5/16	3/8	1/2	5/8	3/4	1
			Emulsion	Compressed Air	MQL	5%	10%	25%	50%	*Profile Milling at ≥ 50% ap is not recommended for diameters 1/4" and below.								
						2.3	1.8	1.2	1.0	← Multiply fz by this Factor based on ae. When finishing, use the standard fz per chart below. Only add chip thinning when roughing or semi-finishing.								
vc - SFM										fz - in/tooth								
Low Carbon Steels 1018, 1020	P	up to 28 Rc	●	●	●	1475	1150	980	500	.0012	.0020	.0024	.0031	.0039	.0047	.0060	.0078	.0100
Medium Carbon Steels 1140, 1145	P	28 to 38 Rc	●	●	●	1130	900	830	250	.0012	.0020	.0024	.0031	.0039	.0047	.0060	.0078	.0100
Alloy Steels 4140, 4145	P	28 to 44 Rc	●	●	●	1035	840	755	250	.0012	.0020	.0024	.0031	.0039	.0047	.0060	.0078	.0100
Die / Tool Steels A2, D2, H13, P20	P	28 to 44 Rc	●	●	●	900	725	615	200	.0012	.0020	.0024	.0031	.0039	.0047	.0060	.0078	.0100
Hardened Steels A2, D2	H	45 to 50 Rc	●	○	○	610	495	325	250	.0006	.0010	.0012	.0016	.0020	.0024	.0030	.0040	.0050
Hardened Steels A2, D2	H	50 to 55 Rc	●	○	○	510	410	280	200	.0003	.0005	.0006	.0008	.0010	.0012	.0016	.0020	.0024
Stainless Steel - Easy to Machine 430F, 301, 303, 410, 416 Annealed, 420F, 430	M	up to 28 Rc	●	x	○	675	545	425	360	.0012	.0020	.0024	.0031	.0039	.0047	.0060	.0078	.0100
Stainless Steel - Austenitic 301, 302, 303 High Tensile, 304, 304L, 305, 420, 15-5PH, 17-4PH, 17-7PH	M	up to 28 Rc	●	x	○	525	430	400	210	.0012	.0020	.0024	.0031	.0039	.0047	.0060	.0078	.0100
Stainless Steel - Difficult to Machine 302B, 304B, 309, 310, 316, 316B, 316L, 316Ti, 317, 317L, 321	M	up to 28 Rc	●	x	○	410	330	295	210	.0012	.0020	.0024	.0031	.0039	.0047	.0060	.0078	.0100
Stainless Steel - Difficult to Machine 17-4 PH, PH13-8Mo, Nitronics	M	over 28 Rc	●	x	○	525	430	395	110	.0006	.0010	.0012	.0016	.0020	.0024	.0030	.0040	.0050
Cobalt Chrome Alloys	M		●	x	○	410	325	295	130	.0006	.0010	.0012	.0016	.0020	.0024	.0030	.0040	.0050
Duplex (22%)	M		●	x	○	245	195	180	130	.0006	.0010	.0012	.0016	.0020	.0024	.0030	.0040	.0050
Super Duplex (25%)	M		●	x	○	245	195	180	110	.0006	.0010	.0012	.0016	.0020	.0024	.0030	.0040	.0050
High Temp Alloys	S	up to 42 Rc	●	x	x	180	150	130	85	.0003	.0005	.0006	.0008	.0010	.0012	.0016	.0020	.0024
Inconel	S		●	x	x	180	150	130	85	.0003	.0005	.0006	.0008	.0010	.0012	.0016	.0020	.0024
Titanium Alloys 6Al-4V, 5Al-2.5 Sn, 6Al-2 Sn-4Zr-6Mo, 3Al-8V-6Cr-4Mo-4Zr, 10V-2Fe-3Al, 13V-11Cr-3Al	S	up to 42 Rc	●	x	x	375	350	330	175	.0003	.0005	.0006	.0008	.0010	.0012	.0016	.0020	.0024
Cast-Iron - Gray CG, ASTM A48, CLASS 20, 25, 30, 35, SAE J431C, GRADES G1800, G3000, G3500, GG 10, 15, 20, 25, 30, 35, 40	K	up to 240 HB	●	○	○	1625	1295	870	350	.0012	.0020	.0024	.0031	.0039	.0047	.0060	.0078	.0100
Cast Iron - Ductile & Malleable CGI 60-40-18, 65-45-12, D4018, D4512, D5506, 32510, 35108, M3210, M4504, M5503, 250, 300, 350, 400, 450	K	over 240 HB	●	○	○	675	540	510	260	.0012	.0020	.0024	.0031	.0039	.0047	.0060	.0078	.0100

Spindle Maximum - Should the calculated spindle speed be more than your actual spindle maximum, use this formula:  
 (Calculated Feed x Spindle Maximum)/Calculated Speed.

Technical data provided should be considered advisory only as variations may be necessary depending on the particular application.

# TuffCut® XT

## 278 / 278CB / 278N Series Recommended Cutting Data - Profile Milling - Metric

Workpiece Material Group	ISO	Hardness	Coolant			Profiling (ae)*				End Mill Diameter (mm)								
			● Preferred ○ Possible x Not Possible							3*	5*	6*	8	10	12	16	20	25
			Emulsion	Compressed Air	MQL	5%	10%	25%	50%	*Profile Milling at ≥ 50% ap is not recommended for diameters 6mm and below.								
							vc - m/min				← Multiply fz by this Factor based on ae. When finishing, use the standard fz per chart below. Only add chip thinning when roughing or semi-finishing.							
										fz - mm/tooth								
Low Carbon Steels 1018, 1020	P	up to 28 Rc	●	●	●	450	350	300	150	.0300	.0500	.0600	.0800	.1000	.1200	.1600	.2000	.2500
Medium Carbon Steels 1140, 1145	P	28 to 38 Rc	●	●	●	345	275	255	75	.0300	.0500	.0600	.0800	.1000	.1200	.1600	.2000	.2500
Alloy Steels 4140, 4145	P	28 to 44 Rc	●	●	●	315	255	230	75	.0300	.0500	.0600	.0800	.1000	.1200	.1600	.2000	.2500
Die / Tool Steels A2, D2, H13, P20	P	28 to 44 Rc	●	●	●	275	220	185	60	.0300	.0500	.0600	.0800	.1000	.1200	.1600	.2000	.2500
Hardened Steels A2, D2	H	45 to 50 Rc	●	○	○	185	150	100	75	.0150	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250
Hardened Steels A2, D2	H	50 to 55 Rc	●	○	○	155	125	85	60	.0070	.0120	.0150	.0200	.0250	.0300	.0400	.0500	.0620
Stainless Steel - Easy to Machine 430F, 301, 303, 410, 416 Annealed, 420F, 430	M	up to 28 Rc	●	x	○	205	165	130	110	.0300	.0500	.0600	.0800	.1000	.1200	.1600	.2000	.2500
Stainless Steel - Austenitic 301, 302, 303 High Tensile, 304, 304L, 305, 420, 15-5PH, 17-4PH, 17-7PH	M	up to 28 Rc	●	x	○	160	130	120	65	.0300	.0500	.0600	.0800	.1000	.1200	.1600	.2000	.2500
Stainless Steel - Difficult to Machine 302B, 304B, 309, 310, 316, 316B, 316L, 316Ti, 317, 317L, 321	M	up to 28 Rc	●	x	○	125	100	90	65	.0300	.0500	.0600	.0800	.1000	.1200	.1600	.2000	.2500
Stainless Steel - Difficult to Machine 17-4 PH, PH13-8Mo, Nitronics	M	over 28 Rc	●	x	○	160	130	120	35	.0150	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250
Cobalt Chrome Alloys	M		●	x	○	125	100	90	40	.0150	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250
Duplex (22%)	M		●	x	○	75	60	55	40	.0150	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250
Super Duplex (25%)	M		●	x	○	75	60	55	35	.0150	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250
High Temp Alloys	S	up to 42 Rc	●	x	x	55	45	40	25									
Inconel	S		●	x	x	55	45	40	25									
Titanium Alloys 6Al-4V, 5Al-2.5 Sn, 6Al-2 Sn-4Zr-6Mo, 3Al-8V-6Cr4Mo-4Zr, 10V-2Fe-3Al, 13V-11Cr-3Al	S	up to 42 Rc	●	x	x	115	105	100	55	.0070	.0120	.0150	.0200	.0250	.0300	.0400	.0500	.0620
Cast-Iron - Gray CG, ASTM A48, CLASS 20, 25, 30, 35, SAE J431C, GRADES G1800, G3000, G3500, GG 10, 15, 20, 25, 30, 35, 40	K	up to 240 HB	●	○	○	495	395	265	110	.0300	.0500	.0600	.0800	.1000	.1200	.1600	.2000	.2500
Cast Iron - Ductile & Malleable CGI 60-40-18, 65-45-12, D4018, D4512, D5506, 32510, 35108, M3210, M4504, M5503, 250, 300, 350, 400, 450	K	over 240 HB	●	○	○	205	165	155	80	.0300	.0500	.0600	.0800	.1000	.1200	.1600	.2000	.2500

Spindle Maximum - Should the calculated spindle speed be more than your actual spindle maximum, use this formula:  
(Calculated Feed x Spindle Maximum)/Calculated Speed.

Technical data provided should be considered advisory only as variations may be necessary depending on the particular application.

## TuffCut® XT

### 278 / 278CB / 278N Series Recommended Cutting Data - Slotting - Inch

Workpiece Material Group	ISO	Hardness	Coolant			Slotting*			End Mill Diameter (inch)									
			● Preferred ○ Possible x Not Possible						1/8*	3/16*	1/4*	5/16	3/8	1/2	5/8	3/4	1	
			Emulsion	Compressed Air	MQL	25%	50%	100%	*Slotting at > 25% ap is not recommended for diameters 1/4" and below.									
			vc - SFM			fz - in/tooth												
Low Carbon Steels 1018, 1020	P	up to 28 Rc	●	●	●	550	500	475	.0004	.0010	.0012	.0016	.0020	.0025	.0031	.0040	.0050	
Medium Carbon Steels 1140, 1145	P	28 to 38 Rc	●	●	●	275	250	225	.0004	.0010	.0012	.0016	.0020	.0025	.0031	.0040	.0050	
Alloy Steels 4140, 4145	P	28 to 44 Rc	●	●	●	275	250	225	.0004	.0010	.0012	.0016	.0020	.0025	.0031	.0040	.0050	
Die / Tool Steels A2, D2, H13, P20	P	28 to 44 Rc	●	●	●	225	200	175	.0004	.0010	.0012	.0016	.0020	.0025	.0031	.0040	.0050	
Hardened Steels A2, D2	H	45 to 50 Rc	●	○	○	275	250	225	.0003	.0005	.0006	.0008	.0010	.0012	.0016	.0020	.0024	
Hardened Steels A2, D2	H	50 to 55 Rc	●	○	○	225	200	175	.0001	.0002	.0003	.0004	.0005	.0006	.0008	.0010	.0015	
Stainless Steel - Easy to Machine 430F, 301, 303, 410, 416 Annealed, 420F, 430	M	up to 28 Rc	●	x	○	385	360	350	.0002	.0004	.0008	.0012	.0014	.0018	.0022	.0026	.0038	
Stainless Steel - Austenitic 301, 302, 303 High Tensile, 304, 304L, 305, 420, 15-5PH, 17-4PH, 17-7PH	M	up to 28 Rc	●	x	○	225	210	200	.0002	.0004	.0008	.0012	.0014	.0018	.0022	.0026	.0038	
Stainless Steel - Difficult to Machine 302B, 304B, 309, 310, 316, 316B, 316L, 316Ti, 317, 317L, 321	M	up to 28 Rc	●	x	○	225	210	200	.0002	.0004	.0008	.0012	.0014	.0018	.0022	.0026	.0038	
Stainless Steel - Difficult to Machine 17-4 PH, PH13-8Mo, Nitronics	M	over 28 Rc	●	x	○	125	110	100	.0003	.0005	.0006	.0008	.0010	.0012	.0016	.0020	.0024	
Cobalt Chrome Alloys	M		●	x	○	150	130	120	.0003	.0005	.0006	.0008	.0010	.0012	.0016	.0020	.0024	
Duplex (22%)	M		●	x	○	150	130	120	.0003	.0005	.0006	.0008	.0010	.0012	.0016	.0020	.0024	
Super Duplex (25%)	M		●	x	○	120	110	100	.0003	.0005	.0006	.0008	.0010	.0012	.0016	.0020	.0024	
High Temp Alloys	S	up to 42 Rc	●	x	x	100	85	75	.0003	.0005	.0006	.0008	.0010	.0012	.0016	.0020	.0024	
Inconel	S		●	x	x	95	85	75	.0003	.0005	.0006	.0008	.0010	.0012	.0016	.0020	.0024	
Titanium Alloys 6Al-4V, 5Al-2.5 Sn, 6Al-2 Sn-4Zr-6Mo, 3Al-8V-6Cr-4Mo-4Zr, 10V-2Fe-3Al, 13V-11Cr-3Al	S	up to 42 Rc	●	x	x	180	175	160	.0003	.0005	.0006	.0008	.0010	.0012	.0016	.0020	.0024	
Cast-Iron - Gray CG, ASTM A48, CLASS 20, 25, 30, 35, SAE J431C, GRADES G1800, G3000, G3500, GG 10, 15, 20, 25, 30, 35, 40	K	up to 240 HB	●	○	○	375	350	325	.0004	.0010	.0012	.0016	.0020	.0024	.0031	.0040	.0050	
Cast Iron - Ductile & Malleable CGI 60-40-18, 65-45-12, D4018, D4512, D5506, 32510, 35108, M3210, M4504, M5503, 250, 300, 350, 400, 450	K	over 240 HB	●	○	○	275	260	250	.0004	.0010	.0012	.0016	.0020	.0024	.0031	.0040	.0050	

Spindle Maximum - Should the calculated spindle speed be more than your actual spindle maximum, use this formula:  
 (Calculated Feed x Spindle Maximum)/Calculated Speed.

Technical data provided should be considered advisory only as variations may be necessary depending on the particular application.

End Mills - Technical Information  
Series 278 / 278CB / 278N

# TuffCut® XT

## 278 / 278CB / 278N Series Recommended Cutting Data - Slotting - Metric

Workpiece Material Group	ISO	Hardness	Coolant			Slotting*			End Mill Diameter (mm)								
			● Preferred ○ Possible x Not Possible						3*	5*	6*	8	10	12	16	20	25
			Emulsion	Compressed Air	MQL	25%	50%	100%	*Slotting at > 25% ap is not recommended for diameters 6mm and below.								
						vc - m/min			fz - mm/tooth								
Low Carbon Steels 1018, 1020	P	up to 28 Rc	●	●	●	170	150	145	.0100	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250
Medium Carbon Steels 1140, 1145	P	28 to 38 Rc	●	●	●	85	75	70	.0100	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250
Alloy Steels 4140, 4145	P	28 to 44 Rc	●	●	●	85	75	70	.0100	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250
Die / Tool Steels A2, D2, H13, P20	P	28 to 44 Rc	●	●	●	70	60	55	.0100	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250
Hardened Steels A2, D2	H	45 to 50 Rc	●	○	○	85	75	70	.0070	.0120	.0150	.0200	.0250	.0300	.0400	.0500	.0620
Hardened Steels A2, D2	H	50 to 55 Rc	●	○	○	70	60	55	.0030	.0060	.0070	.0100	.0120	.0150	.0200	.0250	.0370
Stainless Steel - Easy to Machine 430F, 301, 303, 410, 416 Annealed, 420F, 430	M	up to 28 Rc	●	x	○	120	110	110	.0100	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250
Stainless Steel - Austenitic 301, 302, 303 High Tensile, 304, 304L, 305, 420, 15-5PH, 17-4PH, 17-7PH	M	up to 28 Rc	●	x	○	70	65	60	.0100	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250
Stainless Steel - Difficult to Machine 302B, 304B, 309, 310, 316, 316B, 316L, 316Ti, 317, 317L, 321	M	up to 28 Rc	●	x	○	70	65	60	.0100	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250
Stainless Steel - Difficult to Machine 17-4 PH, PH13-8Mo, Nitronics	M	over 28 Rc	●	x	○	40	35	30	.0070	.0120	.0150	.0200	.0250	.0300	.0400	.0500	.0620
Cobalt Chrome Alloys	M		●	x	○	45	40	40	.0070	.0120	.0150	.0200	.0250	.0300	.0400	.0500	.0620
Duplex (22%)	M		●	x	○	45	40	40	.0070	.0120	.0150	.0200	.0250	.0300	.0400	.0500	.0620
Super Duplex (25%)	M		●	x	○	40	35	30	.0070	.0120	.0150	.0200	.0250	.0300	.0400	.0500	.0620
High Temp Alloys	S	up to 42 Rc	●	x	x	30	25	25	.0070	.0120	.0150	.0200	.0250	.0300	.0400	.0500	.0620
Inconel	S		●	x	x	30	25	25	.0070	.0120	.0150	.0200	.0250	.0300	.0400	.0500	.0620
Titanium Alloys 6Al-4V, 5Al-2.5 Sn, 6Al-2 Sn-4Zr-6Mo, 3Al-8V-6Cr4Mo-4Zr, 10V-2Fe-3Al, 13V-11Cr-3Al	S	up to 42 Rc	●	x	x	55	55	50	.0070	.0120	.0150	.0200	.0250	.0300	.0400	.0500	.0620
Cast-Iron - Gray CG, ASTM A48, CLASS 20, 25, 30, 35, SAE J431C, GRADES G1800, G3000, G3500, GG 10, 15, 20, 25, 30, 35, 40	K	up to 240 HB	●	○	○	115	105	100	.0100	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250
Cast Iron - Ductile & Malleable CGI 60-40-18, 65-45-12, D4018, D4512, D5506, 32510, 35108, M3210, M4504, M5503, 250, 300, 350, 400, 450	K	over 240 HB	●	○	○	85	80	75	.0100	.0250	.0300	.0400	.0500	.0600	.0800	.1000	.1250

Spindle Maximum - Should the calculated spindle speed be more than your actual spindle maximum, use this formula:  
 (Calculated Feed x Spindle Maximum)/Calculated Speed.

Technical data provided should be considered advisory only as variations may be necessary depending on the particular application.