

TuffCut® 3D

XFO Series Recommended Cutting Data - Speeds - Inch

Recommended Speeds by Material Group		Stock Allowance 			Finishing	Semi-Finishing	
Workpiece Material Group	Material Type	Coolant			.01-.03 x D	.05-.07 x D	
		Emulsion	Compressed Air	MQL	Vc-SFM		
Steels	P	Low Carbon	●	●	●	1480	1150
		Medium Carbon	●	●	●	1130	900
		Alloy Steels	●	●	●	1030	840
		Die / Tool Steels (≤ 45 HRC)	●	●	●	900	720
Stainless Steels	M	Free Machining	●	X	○	670	540
		Austenitic	●	X	○	520	430
		Difficult Stainless	●	X	○	410	330
		PH Stainless (≤ 45 HRC)	●	X	○	520	430
		Cobalt Chrome Alloys	●	X	○	410	330
		Duplex (22%)	●	X	○	250	200
		Super Duplex (25%)	●	X	○	200	160
		Special Alloys	S	High Temp Alloys	●	X	X
Titanium Alloys	●	X		X	360	300	

● Preferred ○ Possible X Not Possible

XFO Series Recommended Cutting Data - Feeds - Inch

Recommended Feeds by Material Group		Tool Diameter (inch)								
Workpiece Material Group	Material Type	.2362		.3150		.3937		.4724		
		Semi Finish	Finish	Semi Finish	Finish	Semi Finish	Finish	Semi Finish	Finish	
		Fz - in/tooth								
Steels	P	Low Carbon	.0019	.0012	.0025	.0016	.0031	.0020	.0038	.0024
		Medium Carbon	.0019	.0012	.0025	.0016	.0031	.0020	.0038	.0024
		Alloy Steels	.0019	.0012	.0025	.0016	.0031	.0020	.0038	.0024
		Die / Tool Steels (≤ 45 HRC)	.0014	.0009	.0019	.0013	.0024	.0016	.0028	.0019
Stainless Steels	M	Free Machining	.0019	.0012	.0025	.0016	.0031	.0020	.0038	.0024
		Austenitic	.0019	.0012	.0025	.0016	.0031	.0020	.0038	.0024
		Difficult Stainless	.0019	.0012	.0025	.0016	.0031	.0020	.0038	.0024
		PH Stainless (≤ 45 HRC)	.0014	.0009	.0019	.0013	.0024	.0016	.0028	.0019
		Cobalt Chrome Alloys	.0014	.0009	.0019	.0013	.0024	.0016	.0028	.0019
		Duplex (22%)	.0014	.0009	.0019	.0013	.0024	.0016	.0028	.0019
		Super Duplex (25%)	.0014	.0009	.0019	.0013	.0024	.0016	.0028	.0019
		Special Alloys	S	High Temp Alloys	.0014	.0009	.0019	.0013	.0024	.0016
Titanium Alloys	.0017	.0012		.0022	.0016	.0028	.0020	.0033	.0024	

Notes:

- To prevent chip evacuation issues, utilize 4-flute tools for semi-finishing operations & avoid cutting with the tip of the tool wherever possible.
- Reduced feeds required when cutting with the tip of the tool.

Technical data provided should be considered advisory only as variations may be necessary depending on the particular application.

TuffCut® 3D

XFO Series Recommended Cutting Data - Speeds - Metric

Recommended Speeds by Material Group		Stock Allowance 			Finishing	Semi-Finishing	
Workpiece Material Group	Material Type	Coolant			.01-.03 x D	.05-.07 x D	
		Emulsion	Compressed Air	MQL	Vc - M/Min		
Steels	P	Low Carbon	●	●	●	450	350
		Medium Carbon	●	●	●	345	275
		Alloy Steels	●	●	●	315	255
		Die / Tool Steels (≤ 45 HRC)	●	●	●	275	220
Stainless Steels	M	Free Machining	●	X	○	205	165
		Austenitic	●	X	○	160	130
		Difficult Stainless	●	X	○	125	100
		PH Stainless (≤ 45 HRC)	●	X	○	160	130
		Cobalt Chrome Alloys	●	X	○	125	100
		Duplex (22%)	●	X	○	75	60
		Super Duplex (25%)	●	X	○	60	50
		High Temp Alloys	●	X	X	45	30
Titanium Alloys	●	X	X	110	90		

● Preferred ○ Possible X Not Possible

XFO Series Recommended Cutting Data - Feeds - Metric

Recommended Feeds by Material Group		Tool Diameter (mm)								
Workpiece Material Group	Material Type	6		8		10		12		
		Semi Finish	Finish	Semi Finish	Finish	Semi Finish	Finish	Semi Finish	Finish	
		Fz - mm/tooth								
Steels	P	Low Carbon	.048	.030	.064	.040	.080	.050	.096	.060
		Medium Carbon	.048	.030	.064	.040	.080	.050	.096	.060
		Alloy Steels	.048	.030	.064	.040	.080	.050	.096	.060
		Die / Tool Steels (≤ 45 HRC)	.036	.024	.048	.032	.060	.040	.072	.048
Stainless Steels	M	Free Machining	.048	.030	.064	.040	.080	.050	.096	.060
		Austenitic	.048	.030	.064	.040	.080	.050	.096	.060
		Difficult Stainless	.048	.030	.064	.040	.080	.050	.096	.060
		PH Stainless (≤ 45 HRC)	.036	.024	.048	.032	.060	.040	.072	.048
		Cobalt Chrome Alloys	.036	.024	.048	.032	.060	.040	.072	.048
		Duplex (22%)	.036	.024	.048	.032	.060	.040	.072	.048
		Super Duplex (25%)	.036	.024	.048	.032	.060	.040	.072	.048
Special Alloys	S	High Temp Alloys	.036	.024	.048	.032	.060	.040	.072	.048
		Titanium Alloys	.042	.030	.056	.040	.070	.050	.084	.060


Notes:

- To prevent chip evacuation issues, utilize 4-flute tools for semi-finishing operations & avoid cutting with the tip of the tool wherever possible.
- Reduced feeds required when cutting with the tip of the tool.

Technical data provided should be considered advisory only as variations may be necessary depending on the particular application.

TuffCut® 3D

XFO / XFO-AL Series



End Mills - Technical Information
Series XFO / XFO-AL

Effective Angles

Tool Ø	Nose Radius		Major Radius	
	R1	Effective Angle (Max.)	R2	Effective Angle (Max.)
6	1	78.2°	95	11.8°
8	1	75.1°	90	14.9°
10	2	74.6°	85	15.4°
12	2	71.6°	80	18.4°

*Numbers above represent maximum angle values.

Technical data provided should be considered advisory only as variations may be necessary depending on the particular application.

TuffCut® 3D

XFO / XFO-AL Series

Stepover Distance by Cusp Height - **Inch**

Tool Ø (mm)		Cusp Height (Inch)	.0001	.0002	.0003	.0004	.0005
DC	R2						
6	95	Stepover (Inch)	.059	.077	.097	.109	.124
8	90		.058	.075	.094	.106	.120
10	85		.056	.072	.092	.103	.117
12	80		.054	.070	.089	.100	.113

Stepover Distance by Cusp Height - **Metric**

Tool Ø (mm)		Cusp Height (mm)	0.003	0.005	0.008	0.010	0.013
DC	R2						
6	95	Stepover (mm)	1.50	1.95	2.46	2.76	3.14
8	90		1.47	1.90	2.40	2.69	3.06
10	85		1.43	1.84	2.33	2.61	2.97
12	80		1.38	1.79	2.26	2.53	2.88



Technical data provided should be considered advisory only as variations may be necessary depending on the particular application.